



G.654.C

PureAdvance™-80

Pure Silica Core Single Mode Optical Fiber



- Low attenuation of ≤ 0.17 dB/km and MFD compatible with standard G.652 SMFs
- For terrestrial metro and long-haul networks
- Applicable for high-density terrestrial cables

PureAdvance™-80 (G.654.C)

General

Effective Area

Typical effective area at 1550 nm	85 μm^2
-----------------------------------	--------------------

Attenuation

Typical Attenuation at 1550 nm	0.165 dB/km
--------------------------------	-------------

Core Glass

Pure Silica

Optical Characteristics

Attenuation

Attenuation at 1550 nm	≤ 0.17 dB/km
Attenuation at 1625 nm	≤ 0.20 dB/km
Point discontinuity at 1550 nm	≤ 0.05 dB

Mode Field Diameter (MFD)

MFD at 1550 nm	$10.1 \pm 0.7 \mu\text{m}$
----------------	----------------------------

Chromatic Dispersion

Chromatic dispersion at 1550 nm	≤ 20 ps/nm/km
Chromatic dispersion slope at 1550nm	≤ 0.070 ps/nm ² /km

Cable Cutoff Wavelength (λ_{cc})

λ_{cc}	≤ 1530 nm
----------------	----------------

Polarization Mode Dispersion (PMD)

Individual fiber PMD ^{*1)}	≤ 0.1 ps/r-km
Fiber PMD link design value ^{*2)}	≤ 0.06 ps/r-km

Geometrical Characteristics

Glass Geometry

Core-cladding concentricity error	$\leq 0.8 \mu\text{m}$
Cladding diameter	$125.0 \pm 1.0 \mu\text{m}$
Cladding non-circularity	$\leq 2.0 \%$
Fiber curl radius	≥ 4 m

Coating Geometry

Coating diameter (Natural)	$245 \pm 10 \mu\text{m}$
Coating diameter (Colored)	$250 \pm 15 \mu\text{m}$
Coating-cladding concentricity error	$\leq 12 \mu\text{m}$

Mechanical Characteristics

Proof Test

Proof stress level	1.2% (0.86GPa)
--------------------	----------------

Macrobending Loss

Bending radius	Number of turns	Wavelength	Induced Attenuation
30 mm	100	1550 nm	≤ 0.1 dB
30 mm	100	1625 nm	≤ 0.1 dB

Dynamic Fatigue (Nd)

Nd	20
----	----

Environmental Tests

Condition	Induced Attenuation Change at 1550 nm and 1625 nm
-60 to +85°C temperature cycling (IEC60793-1-52)	≤ 0.05 dB/km
-10 to +85°C/98%RH temperature humidity cycling	≤ 0.05 dB/km
+23°C water immersion (IEC60793-1-53)	≤ 0.05 dB/km
+85°C heat aging (IEC60793-1-51)	≤ 0.05 dB/km
+85°C/85%RH damp heat (IEC60793-1-50)	≤ 0.05 dB/km

Packaging

Delivery Length

6.3 – 50.4 km

Performance Characteristics

Effective Group Index of Refraction

Effective group index of refraction at 1550 nm	1.463
--	-------

*1) Measured on fiber with free tension.

*2) Since PMD value may change when fiber is cabled, actual PMD link design value in a cable shall be confirmed by cable manufacturer. Under appropriate cable design, PureAdvance-80 specification supports network design requirements for a 0.20 ps/r-km of maximum cable PMD link design value recommended by ITU-T G.654.C.

This document states a standard specification. Upon request, alternative value offerings will be available.